

Granite[®] PVDF 25 microns

guarantee **15** years
 free of chromates and heavy metals

Properties	<ul style="list-style-type: none"> • Very good colour and appearance stability • Good corrosion resistance • Very good chemical resistance • Thermoplastic paint • Surface treatment and paint: free of hexavalent chromium and heavy metals 																																										
Applications	External uses: buildings in aggressive environments																																										
Description	<table border="1"> <tr> <td>Thickness ⁽¹⁾</td> <td>25 microns</td> </tr> <tr> <td>Gloss (Gardner 60°) ⁽¹⁾</td> <td>30 GU Other gloss levels on request</td> </tr> <tr> <td>Colours</td> <td>Specific colours on request</td> </tr> <tr> <td>Appearance</td> <td>Smooth</td> </tr> <tr> <td>Temporary protection (optional)</td> <td>Self-adhesive film or heat-sealed film</td> </tr> </table>	Thickness ⁽¹⁾	25 microns	Gloss (Gardner 60°) ⁽¹⁾	30 GU Other gloss levels on request	Colours	Specific colours on request	Appearance	Smooth	Temporary protection (optional)	Self-adhesive film or heat-sealed film																																
Thickness ⁽¹⁾	25 microns																																										
Gloss (Gardner 60°) ⁽¹⁾	30 GU Other gloss levels on request																																										
Colours	Specific colours on request																																										
Appearance	Smooth																																										
Temporary protection (optional)	Self-adhesive film or heat-sealed film																																										
Performance	<table border="1"> <tr> <td>Adhesion of the coating (T-bend)</td> <td>≤ 1 T</td> </tr> <tr> <td>Resistance to cracking on bending (T-bend)</td> <td>≤ 2 T</td> </tr> <tr> <td>Impact resistance</td> <td>18 J</td> </tr> <tr> <td>Surface "pencil" hardness</td> <td>HB to H</td> </tr> <tr> <td>Corrosion resistance:</td> <td></td> </tr> <tr> <td>• Salt spray test</td> <td>360 hours</td> </tr> <tr> <td>• Corrosion resistance category</td> <td>RC3</td> </tr> <tr> <td>Condensation resistance:</td> <td></td> </tr> <tr> <td>• QCT test</td> <td>1000 hours</td> </tr> <tr> <td>• Corrosion protection (interior) category</td> <td>CPI3</td> </tr> <tr> <td>UV resistance:</td> <td></td> </tr> <tr> <td>• QUV (UVA + H₂O) test (2000 hours)</td> <td>ΔE ≤ 2; GR ≥ 80%</td> </tr> <tr> <td>• UV resistance category</td> <td>RUV4</td> </tr> <tr> <td>Fire behaviour classification (EN 13501-1)</td> <td>A1</td> </tr> <tr> <td>Resistance to acids and bases</td> <td>Good to very good</td> </tr> <tr> <td>Resistance to solvents:</td> <td></td> </tr> <tr> <td>• Aliphatics and alcohols</td> <td>Very good</td> </tr> <tr> <td>• Ketones</td> <td>Good</td> </tr> <tr> <td>• Aromatics</td> <td>Good to very good</td> </tr> <tr> <td>Resistance to mineral oils</td> <td>Very good</td> </tr> <tr> <td>Maximum continuous operating temperature</td> <td>100°C</td> </tr> </table>	Adhesion of the coating (T-bend)	≤ 1 T	Resistance to cracking on bending (T-bend)	≤ 2 T	Impact resistance	18 J	Surface "pencil" hardness	HB to H	Corrosion resistance:		• Salt spray test	360 hours	• Corrosion resistance category	RC3	Condensation resistance:		• QCT test	1000 hours	• Corrosion protection (interior) category	CPI3	UV resistance:		• QUV (UVA + H ₂ O) test (2000 hours)	ΔE ≤ 2; GR ≥ 80%	• UV resistance category	RUV4	Fire behaviour classification (EN 13501-1)	A1	Resistance to acids and bases	Good to very good	Resistance to solvents:		• Aliphatics and alcohols	Very good	• Ketones	Good	• Aromatics	Good to very good	Resistance to mineral oils	Very good	Maximum continuous operating temperature	100°C
Adhesion of the coating (T-bend)	≤ 1 T																																										
Resistance to cracking on bending (T-bend)	≤ 2 T																																										
Impact resistance	18 J																																										
Surface "pencil" hardness	HB to H																																										
Corrosion resistance:																																											
• Salt spray test	360 hours																																										
• Corrosion resistance category	RC3																																										
Condensation resistance:																																											
• QCT test	1000 hours																																										
• Corrosion protection (interior) category	CPI3																																										
UV resistance:																																											
• QUV (UVA + H ₂ O) test (2000 hours)	ΔE ≤ 2; GR ≥ 80%																																										
• UV resistance category	RUV4																																										
Fire behaviour classification (EN 13501-1)	A1																																										
Resistance to acids and bases	Good to very good																																										
Resistance to solvents:																																											
• Aliphatics and alcohols	Very good																																										
• Ketones	Good																																										
• Aromatics	Good to very good																																										
Resistance to mineral oils	Very good																																										
Maximum continuous operating temperature	100°C																																										
Automatic guarantee	<ul style="list-style-type: none"> • Non-perforation of the sheet metal ≤ 15 years, depending on the external environment • Non-delamination of the paint ≤ 15 years, depending on the external environment • Aesthetic appearance (ΔE ≤ 3; Gloss retention ≥ 80%) ≤ 5 years, depending on the geographic location and the paint colour category 																																										
Remarks	<p>These performance characteristics refer specifically to metallic coating Z225 (guaranteed minimum). If any product (film, oil, foam, glue, paint etc) is to be applied after coil delivery, compatibility with the coating needs to be checked first. Although we take great care to reproduce the same aesthetic aspect on each coil, ArcelorMittal cannot guarantee the visual consistency from one single order item to another. Consequently, you need to consider placing one single order for one building; standard samples can only serve as a guide.</p>																																										

(1) Nominal value, tolerance according to EN 10169